

## AIRFORCE INDUSTRY

Item Name	Item Code	Specification No.	Width (mm)	Thickness (mm)	Breaking Load (Kgf)	Elongation at Break %	Total Ends	Picks/ (inch)	Weave
Tape Nylon 20mm UVR Treated	NWF-485	ADRDE/SPECN/70	20±5.0	1.8 ± 0.2	1350 Min	20-24	120	22	Twill
Tape Nylon 26mm W.R. UVR Treated	NWF-31	ADRDE/SPECN/70	26±1.0	3 Max	2040 Min	-	382	22	D.Plain
Tape Nylon 30mm W.R. UVR Treated	NWF-30	ADRDE/SPECN/70	30±1.0	4 Max	3135 Min	-	594	16	D.Plain
Webb Nylon 40mm W.R. UVR Treated	NWF-27	ADRDE/SPECN /1997/47	40±1.0	4 Max	4750 Min	-	529	12	D.Plain
Webb Poly 40mm UVR Treated	NWF-26	ADRDE/SPECN/69	40±1.0	3.8 Max	4750 Min	14 Max	210	11	D.Plain
Nylon Purchase Tape	NWF-822	MIL-T-81736/80	205±4-5	9.01 Max	56700 Min	-	1260	13	D.Plain
Cord Nylon Braided 1800 Kgf	BC-217	ADRDE/SPECN/80	-	-	1800 Min	27±3	-	2	Braided
Cord Nylon Braided 12740 N	BC-148	ADRDE/SPECN /1984/17	-	-	1300 Min	25-30	-	2	Braided
Cord Poly Sheet Para Aramid Bs-5000 Kgf U/D	BC-219	ADRDE/QMS/ TDTM/C/2003/02	12 Max	-	5000 Min	5 Max	-	17	Braided
Cord Poly Sheet Para Aramid Bs-5000 Kgf Black	BC-346 UVR Treated	ADRDE/QMS/ TDTM/C/2003/03	12 Max	-	5000	10 Max	-	8.5	Braided